



Office de la Propriété  
Intellectuelle  
du Canada

Un organisme  
d'Industrie Canada

Canadian  
Intellectual Property  
Office

An agency of  
Industry Canada

CA 2403204 A1 2001/09/20

(21) **2 403 204**

(12) **DEMANDE DE BREVET CANADIEN  
CANADIAN PATENT APPLICATION**

(13) **A1**

(86) Date de dépôt PCT/PCT Filing Date: 2001/03/09  
(87) Date publication PCT/PCT Publication Date: 2001/09/20  
(85) Entrée phase nationale/National Entry: 2002/09/13  
(86) N° demande PCT/PCT Application No.: GB 2001/001040  
(87) N° publication PCT/PCT Publication No.: 2001/068291  
(30) Priorités/Priorities: 2000/03/17 (0006581.3) GB;  
2000/10/03 (09/677,757) US

(51) Cl.Int.<sup>7</sup>/Int.Cl.<sup>7</sup> B22C 1/16, B22C 9/04

(71) Demandeurs/Applicants:  
DUFFEY, DANIEL JAMES, GB;  
SHAW, RICHARD DUDLEY, GB

(72) Inventeurs/Inventors:  
DUFFEY, DANIEL JAMES, GB;  
SHAW, RICHARD DUDLEY, GB

(74) Agent: KIRBY EADES GALE BAKER

(54) Titre : PERFECTIONNEMENTS PORTANT SUR UN MOULAGE A LA CIRE PERDUE  
(54) Title: INVESTMENT CASTING MOULD

(57) Abrégé/Abstract:

A method of investment casting is disclosed, which comprises the preparation of a refractory slurry by mixing a binder, a refractory material, and a quantity of water-insoluble organic fibres, and the application of one or more coats of this slurry to an expendable pattern, so as to build up a shell. It has been found that each coat of the slurry thus formed is surprisingly thick, and that a relatively short drying time is required for each coat, hence enabling a shell of desirable thickness to be rapidly built in a small number of "dipping cycles". The invention also encompasses a kit of ingredients for putting the method of the invention into effect; a shell produced in accordance with this method; and a refractory slurry for use in this method.



## (12) INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(19) World Intellectual Property Organization  
International Bureau(43) International Publication Date  
20 September 2001 (20.09.2001)

PCT

(10) International Publication Number  
**WO 01/68291 A3**

- (51) International Patent Classification<sup>7</sup>: **B22C 1/16, 9/04**
- (21) International Application Number: **PCT/GB01/01040**
- (22) International Filing Date: **9 March 2001 (09.03.2001)**
- (25) Filing Language: **English**
- (26) Publication Language: **English**
- (30) Priority Data:  
0006581.3 17 March 2000 (17.03.2000) GB  
09/677,757 3 October 2000 (03.10.2000) US
- (71) Applicants and  
(72) Inventors: **DUFFEY, Daniel, James** [GB/GB]; 76A Ranelagh Road, Ealing, London W5 5RP (GB). **SHAW, Richard, Dudley** [GB/GB]; Dunedin, High Elms Road, Downe, Kent BR6 7JN (GB).
- (74) Agent: **CRUMP, Julian, Richard, John**; FJ Cleveland, 40-43 Chancery Lane, London WC2A 1JQ (GB).
- (81) Designated States (*national*): AE, AG, AL, AM, AT, AU, AZ, BA, BB, BG, BR, BY, BZ, CA, CH, CN, CR, CU, CZ, DE, DK, DM, DZ, EE, ES, FI, GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MA, MD, MG, MK, MN, MW, MX, MZ, NO, NZ, PL, PT, RO, RU, SD, SE, SG, SI, SK, SL, TJ, TM, TR, TT, TZ, UA, UG, US, UZ, VN, YU, ZA, ZW.
- (84) Designated States (*regional*): ARIPO patent (GH, GM, KE, LS, MW, MZ, SD, SL, SZ, TZ, UG, ZW), Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent (AT, BE, CH, CY, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE, TR), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, GW, ML, MR, NE, SN, TD, TG).
- Published:  
— with international search report
- (88) Date of publication of the international search report:  
27 December 2001
- For two-letter codes and other abbreviations, refer to the "Guidance Notes on Codes and Abbreviations" appearing at the beginning of each regular issue of the PCT Gazette.*

**WO 01/68291 A3**(54) Title: **INVESTMENT CASTING MOULD**

(57) Abstract: A method of investment casting is disclosed, which comprises the preparation of a refractory slurry by mixing a binder, a refractory material, and a quantity of water-insoluble organic fibres, and the application of one or more coats of this slurry to an expendable pattern, so as to build up a shell. It has been found that each coat of the slurry thus formed is surprisingly thick, and that a relatively short drying time is required for each coat, hence enabling a shell of desirable thickness to be rapidly built in a small number of "dipping cycles". The invention also encompasses a kit of ingredients for putting the method of the invention into effect; a shell produced in accordance with this method; and a refractory slurry for use in this method.

## IMPROVEMENTS IN AND RELATING TO INVESTMENT CASTING

- The present invention relates to improvements in and relating to investment casting. In particular, the invention relates to a method of investment casting which involves the successive application of one or more coats of a refractory slurry to an expendable pattern, so as to build up a shell. The present invention further provides a refractory slurry for use in the method of the invention, and a kit of ingredients for putting the method of the invention into effect.
- 10 The process of investment casting, otherwise known as the lost wax process, is well known and widely used. Typically, the process involves dipping a wax model into a slurry comprising a binder and a refractory material, so as to coat the model with a layer of slurry; applying a stucco coating of dry refractory to the surface of the layer; allowing the resulting stuccoed slurry layer to dry; and applying further
- 15 stuccoed slurry layers as appropriate to create a shell mould around the wax model having a suitable thickness. After thorough drying, the wax model is eliminated from the shell mould, and the mould is fired.
- Environmental considerations dictate that the binder used in the investment casting process should be water-based, rather than alcohol-based. Customarily, the binder used comprises an aqueous colloidal silica sol. When combined with a suitable refractory material into a slurry, aqueous silica sols are capable of gelling and drying to form a green shape having an acceptable degree of green strength.
- 20 However, where an unmodified aqueous silica sol is used, the time taken for this process is disadvantageously long. A single stuccoed slurry layer, applied to a wax model in the course of investment casting, may take between 3-8 hours to dry.
- 25

Where the model comprises recessed parts or other complex configurations, the drying time may be increased to 24 hours or more. During production of a shell mould having several stuccoed layers, this time must be multiplied by the number of coats applied. Typically, 4-8 coats are required in order to build a shell of acceptable thickness, thereby bringing the total production time to the order of between 12 hours and several days.

Considerable effort has therefore been devoted in the prior art towards accelerating the coat drying time. Thus, for example, EP-A-0638379 discloses that the addition to a colloidal silica sol binder of an elastomeric polymer, such as styrene butadiene, results in a significant reduction in the drying time and an improvement in green strength. The addition of soluble organic polymers to a colloidal silica sol binder for use in investment casting is also disclosed in US 4996084. Soluble organic polymers however readily "wet out", and it has been found that the green strength of a shell mould comprising such polymers is temporarily reduced by the permeation of steam through the mould, for example during the elimination of the wax model from the mould. Moreover, soluble organic polymers are expensive, and their use in investment casting may significantly increase the cost of this process.

It remains therefore a desirable object to provide an alternative means for reducing the time required to build a shell mould of suitable thickness during the process of investment casting.

According to one aspect of the present invention, therefore, there is provided a method of investment casting, comprising the steps of mixing a binder, a

refractory material, and a quantity of water-insoluble organic fibres to form a slurry; coating an expendable pattern with a coat of said slurry; and drying said coat or allowing said coat to dry to form a shell.

- 5     Optionally, a plurality of coats may be applied successively to said expendable pattern, each coat being partly or wholly dried or allowed to dry prior to the application of the next coat. Typically, between 2-10 coats, more preferably 3-8 coats, still more preferably 3, 4 or 5 coats, are successively applied to said pattern. In some embodiments, said expendable pattern is precoated in accordance with  
10     known conventional methods with a coat of slurry comprising no water-insoluble organic fibres, prior to the application in accordance with the present invention of one or more coats of fibre-modified slurry.

- According to a further aspect of the present invention, there is provided a slurry  
15     comprising a binder, a refractory material and a quantity of water-insoluble organic fibres, which slurry is adapted for use in the method of the present invention.

- According to yet another aspect of the present invention, there is provided a kit  
20     adapted for putting the method of the present invention into effect, said kit comprising a quantity of a binder, a quantity of a refractory material, and a quantity of water-insoluble organic fibres; said binder, refractory material and fibres being adapted to be mixed to form a slurry in accordance with the present invention. Said refractory material may be packaged and/or supplied separately  
25     from the other ingredients of the kit. Alternatively, said binder may be packaged and/or supplied separately from the other ingredients of the kit. Optionally, said

fibres may be dispersed in said binder. Alternatively, said fibres may be mixed with said refractory.

5 Surprisingly, the present inventors have found that a refractory slurry comprising a quantity of water-insoluble organic fibres is capable of forming significantly thicker coats around dipped objects than are slurries of the types known in the prior art. An increase in coat thickness obviously implies a concomitant decrease in the number of dipping cycles required to build a mould of sufficient thickness, and hence a significant reduction in the rate of refractory mould production. Coats  
10 of fibre-modified slurry are subject to a comparable drying time in comparison with the products of the prior art, and have been found to possess a comparable green strength.

15 It has furthermore been found that the efficacy of elastomer-modified binders of the kind disclosed in EP-A-0638379 and US 4996084 is largely destroyed by exposure of the binders to low temperatures (0°C and below). In contrast to the elastomer-modified compositions of the prior art, however, fibre-modified refractory slurries in accordance with the present invention have been found to be compatible with many types of antifreezes. This will therefore make possible the  
20 addition of antifreeze to binders intended for use in the fibre-modified slurries of the present invention, hence facilitating winter transport and storage of such binders.

25 Advantageously, said fibres are dispersed in said binder prior to the addition of said refractory material. This will promote the formation of a smooth and stable slurry. However, said refractory material may alternatively be added to said binder

prior to the addition of said fibres. Alternatively, said fibres may be mixed with said refractory material prior to the addition of said binder.

Optionally, said expendable pattern may be coated with said slurry by means of pouring said slurry over the pattern. More preferably, however, said pattern may be coated by means of dipping the pattern into a receptacle containing said slurry. Conveniently, a plurality of patterns, which may for example be held on a "tree", may be dipped simultaneously into said receptacle, thereby enabling the simultaneous production of a plurality of shell moulds.

10

Advantageously, a plurality of coats of slurry may be applied successively to said expendable pattern. In accordance with usual practice, each coat of slurry may be stuccoed with a dry refractory material such as an aluminosilicate such as Molochite® (available from English China Clay), or mullite (available from Cermatco), or zircon, or fused silica, prior to the application of the next coat. Additionally, or in the alternative, one or more of the coats, typically one or more of the outermost coats, may be stuccoed with small polystyrene beads. This will serve to improve the insulating properties of said outermost coats. Preferably, each coat of slurry may be completely covered with a layer of said dry refractory material or said small polystyrene beads prior to the application of the next coat.

15  
20

Advantageously, said method may further include the step of eliminating said expendable pattern from said shell. Said expendable pattern may conveniently be eliminated by means of heating said shell to a temperature which exceeds the melting point of said pattern such that the pattern is caused to melt, and draining the pattern from the shell. Alternatively, said pattern may be eliminated by means

25

WO 01/68291

6

of heating said shell to a temperature which exceeds the sublimation or decomposition temperature of said pattern such that the pattern is caused to sublime or decompose, and causing or permitting the pattern to escape from the shell as a gas.

5

Where said pattern comprises a wax model, the wax may, for example, be eliminated from said shell by heating said shell in a wax autoclave, or by flash firing the wax.

10

Preferably, said fibres may be selected such that the step of eliminating said pattern from the shell does not cause the elimination of the fibres from the shell. Thus, where said pattern is to be eliminated by means of heating said shell to an

15

elimination temperature which exceeds the melting point or sublimation temperature or decomposition temperature of said expendable pattern, said fibres may be selected such that the melting point of said fibres exceeds said elimination temperature. This will ensure that the fibres remain intact notwithstanding elimination of the pattern. The retention of said fibres in the shell will serve to maintain the green strength of the shell.

20

Typically, the melting point of said fibres may be in the region of 150-500°C, preferably 180-270°C, still more preferably 220-270°C. Such fibres may be particularly appropriate for use in conjunction with an expendable wax pattern.

25

The method of the present invention may further comprise the step of heating said shell to a firing temperature for firing the shell. Typically, said firing temperature may be in the range from 800°C to 1100°C.



Advantageously, said fibres may be selected such that the melting point of said fibres is lower than said firing temperature, such that said fibres are melted when the shell is fired. Accordingly, said fibres may be eliminated from the shell during or following firing. The elimination of said fibres from the shell will serve to  
5 create porosity in the shell, thereby making possible the escape of expanding gases from the interior of the shell during the subsequent casting of molten metal therein; and hence reducing the likelihood that the shell will crack under internal gas pressure generated at this stage.

10 Said fibres may be spun and cut or milled in accordance with methods well known to the man skilled in the art. In preferred embodiments, the fibres used are of uniform or substantially uniform length, so as to promote the formation of a uniform slurry. Accordingly, each fibre may be less than 3mm in length, and/or greater than 0.25mm in length. Typically, each fibre will be between 0.25mm and  
15 1.5mm in length, most preferably 1-1.5mm in length. However, the fibres used may alternatively be of varying lengths.

In some embodiments, said quantity of fibres constitutes less than 10% by weight of the slurry. Preferably, said quantity of fibres may constitute less than 8%, more  
20 preferably less than 5% (for example, 4%, 3%, 2% or 1%), or still more preferably less than 1% (for example 0.5% or less), by weight of said slurry. The quantity of fibres used will be a factor in determining the viscosity of the slurry; and hence may be selected in each case to attain a slurry viscosity appropriate for the specific use or application intended for the slurry in that case. Where 1mm fibres are used,  
25 the quantity of fibres incorporated into the slurry may advantageously be 15-20g/l of binder. Where 0.5mm fibres are used, the quantity of fibres incorporated into

the slurry may advantageously be 5-80g/l, preferably 20-35g/l, of binder.

Advantageously, the diameter of each fibre may be sufficient to enable the creation of a porous structure in the shell following elimination of the fibres from the shell, so as to allow the escape of gases from the interior of the shell during metal casting. Thus, said fibres may have a denier up to 250. More preferably, said fibres may have a denier in the range 1.5-2.5; more preferably 1.8-2.1. Alternatively, said fibres may be microdenier fibres.

Said fibres may be selected such that the specific gravity of the fibres is equal to or close to the specific gravity of the binder, such that the fibres can be readily and evenly dispersed within said binder. Typically, the specific gravity of said fibres may be in the range 0.5-3, more preferably 0.5-1.5, still more preferably 1-1.5.

The fibre length, quantity of fibres, and quantity of liquid in the slurry may advantageously be selected such that the viscosity of the slurry is in the desired range. Suitably, said desired range of slurry viscosity may be 26-32 seconds measured on a B4 cup (8-12 seconds measured on a Zahn 4 cup). The desired range of slurry viscosity may however be between 10 and 180 seconds measured on a B4 cup, depending on the use to which the slurry is to be put. The viscosity of the slurry may be adjusted during use by the addition of deionised water, in order to compensate for evaporation losses.

Said fibres may, for example, comprise polypropylene fibres. Alternatively, said fibres may comprise other organic water-insoluble fibres such as acrylic, polyester,

modified acrylic, nylon, or viscose/rayon fibres. The attributes of these fibres are set out in Table 1.

Fibre type	Specific gravity	Melting point (°C)	Resistance to acid	Resistance to alkali
Acrylic	1.17	290	Good	Fair
Polypropylene	0.91	165	Good	Good
Modified Acrylic	1.38	185	Good	Fair
Nylon®	1.14	252	Fair	Good
Viscose/ Rayon	1.52	155	Poor	Poor
Polyester	1.38	234	Good	Fair

TABLE 1

Most preferably, fibres with good distributive properties may be used, such as Nylon® or polyester fibres. The above list of fibres is not exhaustive, and any water-insoluble organic fibre with suitable properties known to the skilled man may be used. In particular, bi-component fibres, comprising two or more fibre types woven or welded into each single bi-component fibre strand, may advantageously be used.

Optionally, said slurry may comprise further ingredients, for modifying or improving the properties of the slurry. For example, said slurry may comprise an antifoaming agent, such as an antifoaming agent based on dimethylpolysiloxane, such as WEX proprietary product A10, which is commercially available from  
5 WEX Chemicals, ICG House, Station Approach, Oldfield Lane North, Greenford, Middlesex UB6 0AL, England. Additionally or alternatively, said slurry may comprise elastomers and/or water-soluble polymers such as styrene butadiene latex. Said slurry may also comprise one or more wetting agents, such as bis(polyoxyethylene) 2-ethylhexylphosphate (commercially available under the  
10 Registered Trade Mark VICTAWET).

In some embodiments, a quantity of graphite and/or antracite particles and a quantity of fused silica may be incorporated in said slurry. Optionally, said graphite and/or antracite particles and fused silica may be incorporated in said  
15 slurry only prior to the application of the outermost coat or coats to said model. The graphite will serve to increase the strength of said coat or coats during wax melt out and drying. The presence of fused silica, having a low thermal conductivity, will serve to improve the insulating properties of the outermost coat or coats.

20 In particularly preferred embodiments, said binder comprises a colloidal silica sol. Said silica sol may be alkaline, and may for example have a pH in the range 9.3 - 10.5, preferably 10.1-10.5. Alternatively, said silica sol may be acidic, whether triple deionised or not. Said silica sol may comprise 10-50% wt/wt silica, typically  
25 20-30% wt/wt silica. Suitable binders for this purpose are widely available commercially; for example LUDOX® (available from Du Pont), or WEXCOAT®

(available from Wex Chemicals at the address given above). Optionally, further components such as phosphates may be included in said binder.

Alternatively, said binder may comprise an acid or alkali hydrolysed ethyl silicate  
5 binder, of the kind known in the art.

Said refractory may comprise aluminosilicates, magnesia, zircon, fused silica and/or other refractory materials well-known to the man skilled in the art. Typically, the amount of refractory used may comprise 100-500% wt/wt, more  
10 preferably 100-200% wt/wt, still more preferably about 150% wt/wt, of said binder.

### Examples

15 Following is a description, by way of example only, of embodiments of the present invention and methods for putting the invention into effect.

#### Example 1

A slurry in accordance with the invention was produced from the following  
20 components:

#### Silica Sol Binder

An aqueous silica sol comprising 24% SiO<sub>2</sub>, having an specific gravity (relative density) of approximately 1.167 and a nominal particle size of 10 nm at a pH of  
25 10.2, and 0.5% wt/wt antifoam (WEX antifoam A10).

**Refractory**

-200 mesh Molochite® (calcined aluminosilicate, commercially available from English China Clays).

**5 Water-insoluble organic fibres**

Nylon® fibres; 1.8 denier, 1mm length.

The slurry was produced as follows. 20g of Nylon® fibres were added to 1.170kg of the silica sol binder and mixed to disperse the fibres therein. 1.755kg of refractory (3:2 wt/wt ratio of refractory : binder) was added to the resulting fibre-  
10 modified binder. The resulting mix was stirred thoroughly to produce a slurry (0.68% wt/wt fibre:slurry). Following thorough agitation and dispersion, the viscosity of the slurry was tested using a Zahn 4 viscosity measuring cup (result: 10 seconds) and a B4 viscosity measuring cup (result: 30 seconds), in accordance  
15 with standard methods.

The slurry was used in accordance with the method of the present invention to coat a plurality of wax test bars of the kind routinely employed in British Standard test procedure BS 1902. Each bar comprised an oblong block of wax measuring  
20 approximately 20cm by 2.5cm by 0.7cm.

The bars were initially chemically cleaned, washed and dried in accordance with normal good practice, and were pre-coated with a refractory slurry comprising a silica sol binder, a zircon sand refractory, and a water soluble polymer, but  
25 containing no insoluble organic fibres; stuccoed; and dried. Each bar was then dipped into the fibre-modified slurry described above, held for a period of 10 - 20

seconds, and removed. Each bar was immediately stuccoed with Molochite® 30/80 mesh grain and then placed under a fan for 1 hour for drying.

5 After drying, a second coat was applied to each bar. Each bar was re-dipped as described above, stuccoed with Molochite® 16/30 mesh grain, and dried for one hour. Four further coats of slurry and Molochite® 16/30 mesh grain were subsequently applied to each bar in this manner, each coat being allowed a drying time of 1 hour. Thus, a total of six coats were applied to each bar within the course of an 8-hour working day.

10

The coated bars were allowed to dry thoroughly overnight. Thereafter, each bar was placed in an autoclave at 8 bar pressure and 180 °C, such that the wax was melted out to leave a refractory shell. The shells were found to have an average thickness of approximately 8mm; that is, about 20% greater than the average  
15 thickness of shells formed under identical conditions from slurries comprising soluble organic polymers, of the kind known in the prior art.

The permeability of the shells produced in accordance with the method described above was found to be comparable with that of shells available in the prior art.  
20 Moreover the strength per unit thickness of each shell produced as above was found to be at least equivalent to that of shells previously available; each shell having a green MOR (modulus of rupture) of approximately 3.5MPa or 502.8psi. The presence of intact Nylon® fibres in the finished shell served to improve the green strength thereof.

25

The drying time required for each coat of fibre-modified slurry was also

comparable with drying times of elastomer-modified prior art slurries. It is noted that the rate of drying may be increased by the addition of magnesia grain, such as 30/80 calcined MgO, to the stucco.

- 5 Shells made in accordance with the method described above were fired at 1000°C for approximately 1 hour, and were thereafter ready for casting with metal.

### Example 2

- 10 A slurry in accordance with the invention was produced from the following components:

#### Silica Sol Binder

- 15 An aqueous silica sol comprising 24% SiO<sub>2</sub>, having an specific gravity (relative density) of approximately 1.167 and a nominal particle size of 10 nm at a pH of 10.2, and 0.5% wt/wt antifoam.

#### Refractory

- 20 -200 mesh Molochite® (calcined aluminosilicate, commercially available from English China Clays).

#### Water-insoluble organic fibres

Polypropylene fibres; 1.8 denier, 1mm length.

- 25 The slurry was produced as follows. 63g of polypropylene fibres were added to 3.5 litres (4.08kg) of the silica sol binder (18g fibres / litre of binder) and mixed to



disperse the fibres therein. 6.13kg of refractory (3:2 wt/wt ratio of refractory : binder) was added to the resulting fibre-modified binder. The resulting mix was stirred thoroughly to produce a slurry. Following thorough agitation and dispersion, the viscosity of the slurry was tested using a Zahn 4 viscosity measuring cup (result: 10 seconds) and a B4 viscosity measuring cup (result: 30 seconds), in accordance with standard methods

The slurry was used in accordance with the method of the present invention to coat a plurality of wax test bars of the kind routinely employed in British Standard test procedure BS 1902. Each bar comprised an oblong block of wax measuring approximately 20cm by 2.5cm by 0.7cm.

The bars were initially chemically cleaned, washed and dried in accordance with normal good practice, and were pre-coated with a refractory slurry comprising a silica sol binder, a zircon sand refractory, and a water soluble polymer, but containing no insoluble organic fibres; stuccoed; and dried. Each bar was then dipped into the fibre-modified slurry described above, held for a period of 10 - 20 seconds, and removed. Each bar was immediately stuccoed with Molochite® 30/80 mesh grain and then placed under a fan for 1 hour for drying.

After drying, a second coat was applied to each bar. Each bar was re-dipped as described above, stuccoed with Molochite® 16/30 mesh grain, and dried for one hour. Four further coats of slurry and Molochite® 16/30 mesh grain were subsequently applied to each bar in this manner, each coat being allowed a drying time of 1 hour. Thus, a total of six coats were applied to each bar within the course of an 8-hour working day.

The coated bars were allowed to dry thoroughly overnight. Thereafter, each bar was placed in an autoclave at 8 bar pressure and 180 °C, such that the wax was melted out to leave a refractory shell. The shells were found to have an average thickness of approximately 8mm; that is, about 20% greater than the average thickness of shells formed under identical conditions from slurries comprising soluble organic polymers, of the kind known in the prior art. During the autoclaving process, the polypropylene fibres, having a relatively low melting point, melted out of the shell, hence yielding a shell with a somewhat diminished green strength.

The permeability of the shells produced in accordance with the method described above was found to be comparable with that of shells available in the prior art. Moreover the strength per unit thickness of each shell produced as above was found to be at least equivalent to that of shells previously available; each shell having a green MOR (modulus of rupture) of approximately 3.5MPa or 502.8psi.

The drying time required for each coat of fibre-modified slurry was also comparable with drying times of elastomer-modified prior art slurries. It is noted that the rate of drying may be increased by the addition of magnesia grain, such as 30/80 calcined MgO, to the stucco.

Shells made in accordance with the method described above were fired at 1000 °C for approximately 1 hour, and were thereafter ready for casting with metal.

**CLAIMS**

- 1 A method of investment casting, comprising the steps of mixing a binder, a refractory material, and a quantity of water-insoluble organic fibres to form a slurry; coating an expendable pattern with one or more coats of said slurry; and drying said one or more coats or allowing said one or more coats to dry to form a shell.
- 2 A method as claimed in claim 1, wherein the fibres are dispersed in said binder prior to the addition of said refractory material to form said slurry.
- 3 A method as claimed in claim 1, wherein said fibres are mixed with the refractory prior to addition of said binder to form said slurry.
- 4 A method as claimed in any of claims 1-3, wherein said expendable pattern is coated with between 2-10, preferably between 3-5, coats of said slurry.
- 5 A method as claimed in any of claims 1-4, further comprising the step of stuccoing each coat with a layer of a dry refractory material before the application of the next coat.
- 6 A method as claimed in any preceding claim, further comprising the step of removing said expendable pattern from said shell, optionally by heating said shell to a temperature exceeding the melting point, or sublimation or decomposition temperature, of said pattern, such that the pattern is caused to melt, sublime or decompose, and causing or allowing said pattern to escape from the shell.
- 7 A method as claimed in any preceding claim, further comprising the step of

heating said shell to a firing temperature for firing said shell.

8 A method as claimed in claim 7, characterised in that the melting point of said fibres is lower than said firing temperature, such that the fibres are caused to melt during firing of said shell.

9 A method as claimed in any preceding claim, characterised in that the melting point of said fibres exceeds the melting point or decomposition or sublimation temperature of said pattern.

10 A method as claimed in any preceding claim, wherein the quantity of water in said slurry is selected such that the slurry has a viscosity in the range 10-180, preferably 26-32 seconds, measured on a B4 cup.

11 A method as claimed in any preceding claim, wherein said fibres have a denier no greater than 250.

12 A method as claimed in claim 11, wherein said fibres have a denier in the range 1.5-2.5 preferably 1.8-2.1.

13 A method as claimed in any preceding claim, wherein the length of said fibres is less than 3mm and/or greater than 0.25mm, preferably between 1-1.5mm.

14 A method as claimed in any preceding claim, wherein the specific gravity of said fibres is in the range 0.5-3, preferably in the range 1-1.5.

15 A method as claimed in any preceding claim, wherein said water-insoluble organic fibres comprise polypropylene fibres.

16 A method as claimed in any preceding claim, wherein said water-insoluble organic fibres comprise Nylon® fibres.

17 A method as claimed in any preceding claim, wherein said water-insoluble organic fibres comprise bicomponent fibres comprising two or more fibre types woven or welded into each single bicomponent fibre strand.

18 A method as claimed in any preceding claim, characterised in that said quantity of fibres constitutes less than 10%, preferably less than 5%, still more preferably less than 1%, most preferably less than 0.5%, by weight of said slurry.

19 A method as claimed in any preceding claim, further comprising the step of incorporating in said slurry a quantity of elastomers and/or water-soluble polymers.

20 A method as claimed in any preceding claim, further comprising the step of incorporating in said slurry a quantity of an antifoaming agent such as dimethylpolysiloxane.

21 A method as claimed in any preceding claim, further comprising the step of incorporating in said slurry a quantity of an antifreeze.

22 A method as claimed in any preceding claim, further comprising the step of incorporating in said slurry a quantity of one or more wetting agents.

23 A method as claimed in any preceding claim, wherein said binder comprises a colloidal silica sol.

24 A method as claimed in any preceding claim, wherein said refractory

comprises aluminosilicates, magnesia and/or zircon.

25 A method as claimed in any preceding claim, further comprising the step of incorporating in said slurry a quantity of graphite and/or anthracite particles and a quantity of fused silica.

26 A method substantially as hereinbefore described with reference to the Examples.

27 A kit of ingredients for putting the method of any of claims 1-26 into effect, which kit comprises a binder, a refractory material, and a quantity of water-insoluble organic fibres.

28 A kit as claimed in claim 27, wherein said fibres are dispersed in said binder.

29 A kit as claimed in claim 27, wherein said fibres are mixed with said refractory material.

30 A kit as claimed in any of claims 27-29, wherein said binder further comprises an antifreeze.

31 A kit as claimed in any of claims 27-30, wherein said binder further comprises an antifoaming agent such as dimethylpolysiloxane.

32 A kit as claimed in any of claims 27-31, wherein said binder further comprises elastomers and/or water-soluble polymers such as styrene butadiene.

33 A kit as claimed in any of claims 27-32, wherein said binder further comprises

one or more wetting agents, such as bis(polyoxyethylene) 2-ethylhexylphosphate.

34 A kit as claimed in any of claims 27-33, further comprising a quantity of deionised water for adjusting the viscosity of said slurry.

35 A shell produced by the method of any of claims 1-26.

36 A refractory slurry comprising a binder, a refractory material, and a quantity of water-insoluble organic fibres, for use in the method of any of claims 1-26.

37 A refractory slurry recited in claim 36, wherein the quantity of water in said slurry is selected such that the slurry has a viscosity in the range 10-180 seconds, preferably 26-32 seconds, measured on a B4 cup.

THIS PAGE BLANK (USPTO)